

# NBS: Sphere8 LuxSphere System

## FEATURES:

- Biopolymer resin flooring, available in an almost infinite range of colours and blends of colour
- In-built glass fibre base layer
- The system components are designed to be used together to form a FeRFA (The Resin Flooring Association) Type 5 flow applied flooring system, light to medium duty
- Coatings are applied by trowel and roller
- Smooth finish and seamless surface
- Certified emission free flooring (solvent, VOC, heavy metals) under AgBB test report
- Excellent UV stability
- Elastic comfort floor (shore hardness: D50)

## SUBSTRATE:

- Suitable sub-floors include dry concrete, sand/cement screed, anhydrite screed, levelling screed or well-bonded tiles (requires special preparation and primer) or Floating Dry Screed Boards (Knauf Brio, Hugo or FHB).
- The substrate must be load-bearing, sound, and free of loose material, dust, oils, grease, rubber marks and other substances with a separating effect
- The tensile strength of the surface must be 1.5 N/mm<sup>2</sup> on average; compressive strength must be a minimum of 25 N/mm<sup>2</sup>
- Residual moisture (CM Method): 4% (concrete), 2.5% (cement screed), 0.5% (anhydrite). Typical drying times for a new 60mm thick cement screed is 8 weeks, and for a new 60mm thick anhydrite screed is up to 12 weeks
- The substrate is to be prepared by suitable measures such as diamond grinding so that it meets the specified requirements
- Underfloor heating shall be commissioned at least 2 weeks before installation and the heating will have been cycled up and down at least 3 times to force dry the screed and identify any defects. Ensure the advice of the underfloor heating manufacturer and screed supplier is followed in relation to timing of initial switch on of the UFH
- Broken out and missing areas must be filled flush with the surface using suitable epoxy repair compound (specify in section C42). Do not use any form of hydraulic mortar
- Plywood subfloors have increased risk of modular board witness lines appearing in the finished floor over time, hence our recommendation for dry screed board solutions which largely eradicate this effect

## LUXSPHERE BUILD-UP:

Initial coat:	Sphere8 Primer ST/STLV/RAPID
Number of coats:	One
Additional layer:	In-built glass fibre base layer
Number of coats:	One
Levelling coat:	Sphere8 Base Coat D60
Number of coats:	One
Thickness layer:	Sphere8 Body Coat ST/UV+
Number of coats:	One
Colour:	Motion [Sphere8 Collection/Bespoke choice] Solid [most colours on demand]
Finish coat:	Sphere8 Seal WB UV+ Clear
Number of coats:	One - Two
Colour:	Clear

www.sphere8.com

---

# NBS: Sphere8 LuxSphere System

---

USAGE: Suitable for use in areas of light to medium traffic, such as residential environments, the LuxSphere system has enhanced build-up and an extended guarantee

AS STANDARD: System thickness to be 5mm nominal

## GUIDANCE FOR SPHERE8 LUXSPHERE

### OPTIONS:

System:

- System:
- Initial coat of Primer ST/STLV/RAPID, levelling coat of Base Coat D60, thickness layer of Body Coat ST/UV+ and up to two finishing coats of Seal WB UV+ Clear
- Can be laid over most substrates subject to modification of the system build up
- For suspended floors where use of dry screed boards is not possible, wooden (ply) subfloors require fibreglass base layer to minimise visibility of modular board lines
- Anhydrite and flowing self-levelling screeds require pre-treatment before installation by grinding and impregnation with special primer
- Grinding to be undertaken by the screeding contractor
- Cracks require pre-treatment before overlaying to minimise veining in the finish
- Expansion joints must be brought through the floor surface
- Underfloor heating must be commissioned fully before installation (>3 times heat cycling)
- Sphere8 installation checklists must be followed – available from Sphere8 on request
- Motion – 2 colours are combined ( by most colour charts) to give a marbled finish
- Solid – a single colour by most colour charts
- Application time – 4-5 days
- Increased slip resistance (R10/R11) using Diamond Seal Grip sealer as an alternative second seal coat

### APPROVALS:

- Resin Flooring Association: FeRFA Type 5
- British Standards Institution: BS 8204-6
- Slip resistance R9 (standard) /R10 /R11
- Impact toughness – Good
- Chemical Resistance – Good
- Thermal Insulation – (R) 0.03m<sup>2</sup>K/W (standard) – 0.09m<sup>2</sup>K/W (with underlay)
- EN 13501-1 Fire Classification B<sub>fl</sub>-s1
- EN ISO 16000 - AgBB – Emission Free, suitable for indoor use
- Service life in pedestrian use – up to 40 years
- Elasticity 230%
- Sound Damping EN ISO 140 – 6dB (standard) – 20dB (acoustic variant)

### CONTACT:

Sphere8  
Unit 1, Five Eastfields Avenue, London, SW18 1FU

info@sphere8.com  
020 8969 0183